

Product: **2K CLEAR**

Article no. 680 061







Important product characteristics:

- easy to apply
- long pot life
- extremely scratch resistant
- high chemical resistance
- highest weathering resistance
- permanent high gloss
- excellent sag resistance
- excellent flow
- easy to polish

Usage:

- refinishing of parts and spot repair

Application:

-  2 full spray passes
-  flash off between coats: approx. 2 minutes
-  air drying: over night at 70°F (20°C) or
force drying: 25 min. at 140 - 160°F (60°C) object temperature
-  infra-red drying possible
after 16 hours at 70°F (20°C), SprayMax® 2K CLEAR
is easy to polish


Substrate:

- basecoats, direct gloss or metallic

Preparation:

- After 30 minutes drying time, basecoat can be coated with SprayMax® 2K CLEAR.
- Mixing of 2K Clear with hardener:
Take red button from cap, attach to valve on aerosol bottom. Press button with the ball of your hand until stop is reached.
- Shake aerosol for 2 minutes vigorously to mix hardener and clear paint. Spray to test. Pot life: 24 hours.

Application:

-  2 spray passes = 50 - 60 microns

Specific characteristics:

- Type of coating: 2K acrylic resins

Important:

- Pot life: 24 hours
- For professional use only
- Shelf life: 12 months 70°F (20°C)



This product contains isocyanate. Individuals with lung or breathing problems or prior reactions to isocyanates must not be exposed to vapour or spraymist. Before using read all safety information on the aerosol label and the material safety data sheet.

SprayMax® is a registered trade mark of the Peter Kwasny Group.

The information contained in this paper corresponds to our present knowledge and is a guide to our products and their uses. It is not to be understood as a guarantee for certain properties of our products or of their specific applications. The warnings printed on our labels must be respected. Any industrial property rights should be observed. We guarantee product quality under the terms of our general conditions of sale.

Peter Kwasny GmbH
Heilbronner Strasse 96
D-74831 Gundelsheim
Tel.: +49 (0)6269 95-0
Fax: +49 (0)6269 95-80
Email: info@kwasny.de
Internet: www.kwasny.de