










## Glasuret® HS Non-Sanding Sealer, white

**Application:** Wet-on-wet sealer for economical repairs.

**Properties:** No sanding and no drying times; very safe to spray; good weathering resistance.

To use in every mixing ratio with Glasuret Non-Sanding Sealer black 285-49, to get different grey colors. Color formulations are available.

- Remarks:**
- Before filler application, fine sand body-filled areas and old paintwork with P280-320 (dry). Use Guide Coat.
  - Prime sand-throughs with Glasuret 283- etch primer filler or Glasuret 285-16.

	<b>Paint System</b>	
	<b>VOC ready for use</b>	4.5 lbs/gal (540 gms/liter)
	<b>Mixing ratio</b>	2:1 + 30%
	<b>Hardener</b>	100% by vol. 285-38
	<b>Reducer</b>	50% by vol 929-51 or -53
		30% by vol. 352-91 or -216
	<b>Spray viscosity DIN 4 at 68°F / 20°C</b>	16 - 18 s
	<b>Potlife at 68°F / 20°C</b>	2 hours
	<b>Gravity cup Spraying pressure</b>	HVLP gun: 1.2 - 1.3 mm 2.0 - 3.0 bars (30 - 45 psi) / 0.7 bar (10 psi) at the nozzle
		High pressure gun: 1.3 - 1.4 mm 3.0 - 4.0 bars (45 - 60 psi)
	<b>Suction cup Spraying pressure</b>	HVLP gun: 1.8 mm 2.0 - 3.0 bars (30 - 45 psi) / 0.7 bar (10 psi) at the nozzle
		High pressure gun: 1.7 mm 3.0 - 4.0 bars (45 - 60 psi)
	<b>Number of spray coats</b>	1 - 2
	<b>Film thickness</b>	0.5 - 1.5 mils
	<b>Flash-off at 68°F / 20°F</b>	10 mins.

Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous & should be used according to label directions & technical data information. Appropriate respiratory protection should be worn at all times while products are in use—read product label for specific details. Statements & methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only & are not to be interpreted as warranty for events resulting from their use.